

new



QUICK & THICK Multi-Surface Glue

Don't be fooled by the name. Of course it's specifically designed for wood... it's from Titebond, after all. However, this formula is also effective on pottery, ceramic, stone, glass, fabrics and more!

Ideal for woodworking, home repairs & craft projects!

- Strong initial tack
- Excellent strength
- Vertical applications
- Fills small gaps
- Dries clear – Paintable
- Water cleanup

Quick & Thick – No runs, no drips



Ordinary Wood Glues



2X faster
50% less clamp time



3X thicker
No-run, less mess



Dries clear
Invisible glue line



Flexible
Impact-resistant

For more information
1-800-347-GLUE (4583) or titebond.com/quickandthick.

W e r e



QUICK & THICK Multi-Surface Glue

Physical Properties (typical)

Type Thixotropic polyvinyl acetate
State High-viscosity liquid
Color White
Dried film Clear
Solids 60%
Viscosity 36,500 cps
pH 4.8

Calculated VOC 2.4 g/L
Weight/gallon 9.0 lbs.
Chalk temperature* Approximately 50°F.
Flashpoint >200°F.
Freeze/thaw stability Stable up to 2 cycles
Storage life 24 months in tightly closed containers at 75°F.

*Chalk temperature indicates the lowest recommended temperature at which the glue, air and materials can be during application, to assure a good bond.

Application Guidelines

Application temperature: Above 50°F.
Open assembly time: 3-5 minutes (70°F. / 50% RH)
Total assembly time: 10-15 minutes (70°F. / 50% RH)
Minimum required spread: Approximately 6 mils or 250 square feet per gallon.
Required clamping pressure: Enough to bring joints tightly together (generally, 100-150 psi for soft woods, 125-175 psi for medium woods and 175-250 psi for hardwoods).
Methods of application: Plastic bottles for fine applications; glue may also be spread with a roller, spreader or brush.
Cleanup: Damp cloth while glue is wet. Scrape off and sand dried excess.

Bond Strength ASTM D905 (on hard maple)

Temperature	Strength psi	% wood failure
Room Temperature	3,000	7
150°F. Overnight	650	0

Product Features

- 2X Faster – 3X Thicker than traditional PVA glues
- Specifically designed for wood – Also provides strong bonds on pottery, ceramics, stone, fabric, glass and most “craft-type” materials
- Ideal for woodshop, home and craft projects
- Fill small cracks and gaps
- Unaffected by finishes
- Excellent sandability on wood
- Designed for interior projects
- Water cleanup & non-toxic
- Nonflammable – No offensive odor
- Conforms to ASTM D4236

Limitations

Titebond Quick & Thick Multi-Surface Glue is not recommended for exterior use or where moisture is likely. For exterior applications, use Titebond III Ultimate Wood Glue or Titebond II Premium Wood Glue. Not for structural or load bearing applications. One of the substrates being bonded must be porous or semi-porous. Not recommended for photos, washable wearables, metals, plastics or rubber. Do not use when temperature, glue or materials are below 50°F. Freezing may not affect the function of the product but may cause it to thicken. Agitation should restore product to original form. Read SDS before use. For wood, sand glued area thoroughly before staining. Store at room temperature. **KEEP FROM FREEZING. KEEP OUT OF THE REACH OF CHILDREN.**

Ordering Information

Cat. No.	Size	Units per Package	Weight	Packages per Pallet
2403	8 oz. Bottle	12	7.26	160

Important Notice: Our recommendations, if any, for the use of this product are based on tests believed to be reliable. Since the use of this product is beyond the control of the manufacturer, no guarantee or warranty, expressed or implied, is made as to such use or effects incidental to such use, handling or possession or the results to be obtained, whether in accordance with the directions or claimed so to be. The manufacturer expressly disclaims responsibility therefore. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing laws/or patents covering any material or use.

2020 Bruck Street, Columbus, Ohio 43207
CUSTOMER SERVICE 1-800-669-4583
TECH SERVICE 1-800-347-GLUE
www.titebond.com

Franklin International

©2016 Franklin International. All rights reserved

FF1026